

$$m_2 = \frac{C_2 (m_1 + m_2)}{100}$$

Substitution of these equations into the preceding expression yields

$$C_1'' = \frac{\frac{C_1 (m_1 + m_2)}{100}}{\frac{C_1 (m_1 + m_2)}{100} + \frac{C_2 (m_1 + m_2)}{100}} = \frac{C_1}{\frac{C_1}{\rho_1} + \frac{C_2}{\rho_2}}$$

If the densities ρ_1 and ρ_2 are given in units of g/cm^3 , then conversion to units of kg/m^3 requires that we multiply this equation by 10^3 , inasmuch as

$$1 \text{ g/cm}^3 = 10^3 \text{ kg/m}^3$$

Therefore, the previous equation takes the form

$$C_1'' = \frac{C_1}{\frac{C_1}{\rho_1} + \frac{C_2}{\rho_2}} \times 10^3$$

which is the desired expression.

(c) Now we are asked to derive Equation 4.10a. The density of an alloy ρ_{ave} is just the total alloy mass M divided by its volume V

$$\rho_{\text{ave}} = \frac{M}{V}$$

Or, in terms of the component elements 1 and 2