

8.30 This problem asks us to calculate the rupture lifetime of a component fabricated from a low carbon-nickel alloy exposed to a tensile stress of 31 MPa at 649°C. All that we need do is read from the 649°C line in Figure 8.30 the rupture lifetime at 31 MPa; this value is about 10,000 h.