

8.23 Five factors that lead to scatter in fatigue life data are (1) specimen fabrication and surface preparation, (2) metallurgical variables, (3) specimen alignment in the test apparatus, (4) variation in mean stress, and (5) variation in test cycle frequency.