

11.8 It is *not possible* to produce malleable iron in pieces having large cross-sectional dimensions. White cast iron is the precursor of malleable iron, and a rapid cooling rate is necessary for the formation of white iron, which may not be accomplished at interior regions of thick cross-sections.