

11.11 The chief difference between heat-treatable and nonheat-treatable alloys is that heat-treatable alloys may be strengthened by a heat treatment wherein a precipitate phase is formed (precipitation hardening) or a martensitic transformation occurs. Nonheat-treatable alloys are not amenable to strengthening by such treatments.