

13.11 The annealing point is that temperature at which the viscosity of the glass is 10^{12} Pa-s (10^{13} P). From Figure 13.7, these temperatures for the several glasses are as follows:

<u>Glass</u>	<u>Annealing Temperature</u>
Soda-lime	500°C (930°F)
Borosilicate	570°C (1060°F)
96% Silica	930°C (1705°F)
Fused silica	1170°C (2140°F)