

Variability of Material Properties

6.49 The five factors that lead to scatter in measured material properties are the following: (1) test method; (2) variation in specimen fabrication procedure; (3) operator bias; (4) apparatus calibration; and (5) material inhomogeneities and/or compositional differences.