

6.37 We are asked to compute the true strain that results from the application of a true stress of 600 MPa (87,000 psi); other true stress-strain data are also given. It first becomes necessary to solve for n in Equation 6.19. Taking logarithms of this expression and after rearrangement we have

$$\begin{aligned} n &= \frac{\log \sigma_T - \log K}{\log \varepsilon_T} \\ &= \frac{\log (500 \text{ MPa}) - \log (825 \text{ MPa})}{\log (0.16)} = 0.273 \end{aligned}$$

Expressing ε_T as the dependent variable (Equation 6.19), and then solving for its value from the data stipulated in the problem statement, leads to

$$\varepsilon_T = \left(\frac{\sigma_T}{K} \right)^{1/n} = \left(\frac{600 \text{ MPa}}{825 \text{ MPa}} \right)^{1/0.273} = 0.311$$