

Hardness

6.46 (a) We are asked to compute the Brinell hardness for the given indentation. It is necessary to use the equation in Table 6.5 for HB, where $P = 1000$ kg, $d = 2.50$ mm, and $D = 10$ mm. Thus, the Brinell hardness is computed as

$$\begin{aligned} \text{HB} &= \frac{2P}{\pi D \left[D - \sqrt{D^2 - d^2} \right]} \\ &= \frac{(2)(1000 \text{ kg})}{(\pi)(10 \text{ mm}) \left[10 \text{ mm} - \sqrt{(10 \text{ mm})^2 - (2.50 \text{ mm})^2} \right]} = 200.5 \end{aligned}$$

(b) This part of the problem calls for us to determine the indentation diameter d which will yield a 300 HB when $P = 500$ kg. Solving for d from the equation in Table 6.5 gives

$$\begin{aligned} d &= \sqrt{D^2 - \left[D - \frac{2P}{(\text{HB})\pi D} \right]^2} \\ &= \sqrt{(10 \text{ mm})^2 - \left[10 \text{ mm} - \frac{(2)(500 \text{ kg})}{(300)(\pi)(10 \text{ mm})} \right]^2} = 1.45 \text{ mm} \end{aligned}$$