

6.32 The moduli of resilience of the alloys listed in the table may be determined using Equation 6.14. Yield strength values are provided in this table, whereas the elastic moduli are tabulated in Table 6.1.

For steel

$$U_r = \frac{\sigma_y^2}{2E}$$

$$= \frac{(830 \times 10^6 \text{ N/m}^2)^2}{(2)(207 \times 10^9 \text{ N/m}^2)} = 16.6 \times 10^5 \text{ J/m}^3 \quad (240 \text{ in.-lb}_f/\text{in.}^3)$$

For the brass

$$U_r = \frac{(380 \times 10^6 \text{ N/m}^2)^2}{(2)(97 \times 10^9 \text{ N/m}^2)} = 7.44 \times 10^5 \text{ J/m}^3 \quad (108 \text{ in.-lb}_f/\text{in.}^3)$$

For the aluminum alloy

$$U_r = \frac{(275 \times 10^6 \text{ N/m}^2)^2}{(2)(69 \times 10^9 \text{ N/m}^2)} = 5.48 \times 10^5 \text{ J/m}^3 \quad (80.0 \text{ in.-lb}_f/\text{in.}^3)$$

And, for the titanium alloy

$$U_r = \frac{(690 \times 10^6 \text{ N/m}^2)^2}{(2)(107 \times 10^9 \text{ N/m}^2)} = 22.2 \times 10^5 \text{ J/m}^3 \quad (323 \text{ in.-lb}_f/\text{in.}^3)$$