

6.4 We are asked to compute the maximum length of a cylindrical nickel specimen (before deformation) that is deformed elastically in tension. For a cylindrical specimen

$$A_0 = \pi \left(\frac{d_0}{2} \right)^2$$

where d_0 is the original diameter. Combining Equations 6.1, 6.2, and 6.5 and solving for l_0 leads to

$$\begin{aligned} l_0 &= \frac{\Delta l}{\varepsilon} = \frac{\Delta l}{\frac{\sigma}{E}} = \frac{\Delta l E}{\frac{F}{A_0}} = \frac{\Delta l E \pi \left(\frac{d_0}{2} \right)^2}{F} = \frac{\Delta l E \pi d_0^2}{4F} \\ &= \frac{(0.25 \times 10^{-3} \text{ m})(207 \times 10^9 \text{ N/m}^2) (\pi) (10.2 \times 10^{-3} \text{ m})^2}{(4)(8900 \text{ N})} \\ &= 0.475 \text{ m} = 475 \text{ mm (18.7 in.)} \end{aligned}$$