

6.11 We are asked, using the equation given in the problem statement, to verify that the modulus of elasticity values along [110] directions given in Table 3.3 for aluminum, copper, and iron are correct. The  $\alpha$ ,  $\beta$ , and  $\gamma$  parameters in the equation correspond, respectively, to the cosines of the angles between the [110] direction and [100], [010] and [001] directions. Since these angles are  $45^\circ$ ,  $45^\circ$ , and  $90^\circ$ , the values of  $\alpha$ ,  $\beta$ , and  $\gamma$  are 0.707, 0.707, and 0, respectively. Thus, the given equation takes the form

$$\begin{aligned} & \frac{1}{E_{\langle 110 \rangle}} \\ &= \frac{1}{E_{\langle 100 \rangle}} - 3 \left( \frac{1}{E_{\langle 100 \rangle}} - \frac{1}{E_{\langle 111 \rangle}} \right) \left[ (0.707)^2 (0.707)^2 + (0.707)^2 (0)^2 + (0)^2 (0.707)^2 \right] \\ &= \frac{1}{E_{\langle 100 \rangle}} - (0.75) \left( \frac{1}{E_{\langle 100 \rangle}} - \frac{1}{E_{\langle 111 \rangle}} \right) \end{aligned}$$

Utilizing the values of  $E_{\langle 100 \rangle}$  and  $E_{\langle 111 \rangle}$  from Table 3.3 for Al

$$\frac{1}{E_{\langle 110 \rangle}} = \frac{1}{63.7 \text{ GPa}} - (0.75) \left[ \frac{1}{63.7 \text{ GPa}} - \frac{1}{76.1 \text{ GPa}} \right]$$

Which leads to,  $E_{\langle 110 \rangle} = 72.6 \text{ GPa}$ , the value cited in the table.

For Cu,

$$\frac{1}{E_{\langle 110 \rangle}} = \frac{1}{66.7 \text{ GPa}} - (0.75) \left[ \frac{1}{66.7 \text{ GPa}} - \frac{1}{191.1 \text{ GPa}} \right]$$

Thus,  $E_{\langle 110 \rangle} = 130.3 \text{ GPa}$ , which is also the value cited in the table.

Similarly, for Fe

$$\frac{1}{E_{\langle 110 \rangle}} = \frac{1}{125.0 \text{ GPa}} - (0.75) \left[ \frac{1}{125.0 \text{ GPa}} - \frac{1}{272.7 \text{ GPa}} \right]$$

And  $E_{\langle 110 \rangle} = 210.5 \text{ GPa}$ , which is also the value given in the table.