

7.18 In order to determine the maximum possible yield strength for a single crystal of Cu pulled in tension, we simply employ Equation 7.5 as

$$\sigma_y = 2\tau_{\text{crss}} = (2)(0.48 \text{ MPa}) = 0.96 \text{ MPa} \quad (140 \text{ psi})$$