

7.4 For the various dislocation types, the relationships between the direction of the applied shear stress and the direction of dislocation line motion are as follows:

edge dislocation--parallel

screw dislocation--perpendicular

mixed dislocation--neither parallel nor perpendicular