

7.21 Hexagonal close packed metals are typically more brittle than FCC and BCC metals because there are fewer slip systems in HCP.