

7.35 During cold-working, the grain structure of the metal has been distorted to accommodate the deformation. Recrystallization produces grains that are equiaxed and smaller than the parent grains.