

12.43 For this problem, the load is given at which a circular specimen of aluminum oxide fractures when subjected to a three-point bending test; we are then asked to determine the load at which a specimen of the same material having a square cross-section fractures. It is first necessary to compute the flexural strength of the aluminum oxide, Equation 12.7b, and then, using this value, we may calculate the value of  $F_f$  in Equation 12.7a.

From Equation 12.7b

$$\begin{aligned}\sigma_{fs} &= \frac{F_f L}{\pi R^3} \\ &= \frac{(3000 \text{ N})(40 \times 10^{-3} \text{ m})}{(\pi)(5.0 \times 10^{-3} \text{ m})^3} = 306 \times 10^6 \text{ N/m}^2 = 306 \text{ MPa} \quad (42,970 \text{ psi})\end{aligned}$$

Now, solving for  $F_f$  from Equation 12.7a, realizing that  $b = d = 12 \text{ mm}$ , yields

$$\begin{aligned}F_f &= \frac{2\sigma_{fs}d^3}{3L} \\ &= \frac{(2)(306 \times 10^6 \text{ N/m}^2)(15 \times 10^{-3} \text{ m})^3}{(3)(40 \times 10^{-3} \text{ m})} = 17,200 \text{ N} \quad (3870 \text{ lbf})\end{aligned}$$