

16.2 This problem asks for the maximum and minimum thermal conductivity values for a TiC-Ni cermet. Using a modified form of Equation 16.1 the maximum thermal conductivity k_{\max} is calculated as

$$\begin{aligned} k_{\max} &= k_m V_m + k_p V_p = k_{\text{Ni}} V_{\text{Ni}} + k_{\text{TiC}} V_{\text{TiC}} \\ &= (67 \text{ W/m-K})(0.10) + (27 \text{ W/m-K})(0.90) = 31.0 \text{ W/m-K} \end{aligned}$$

Using a modified form of Equation 16.2, the minimum thermal conductivity k_{\min} will be

$$\begin{aligned} k_{\min} &= \frac{k_{\text{Ni}} k_{\text{TiC}}}{V_{\text{Ni}} k_{\text{TiC}} + V_{\text{TiC}} k_{\text{Ni}}} \\ &= \frac{(67 \text{ W/m-K})(27 \text{ W/m-K})}{(0.10)(27 \text{ W/m-K}) + (0.90)(67 \text{ W/m-K})} \\ &= 28.7 \text{ W/m-K} \end{aligned}$$