

15.9 (a) The fatigue limits for PMMA and the steel alloy are 10 MPa (1450 psi) and 290 MPa (42,200 psi), respectively.

(b) At 10^6 cycles, the fatigue strengths for nylon 6 and 2014-T6 aluminum are 11 MPa (1600 psi) and 200 MPa (30,000 psi), respectively.